

Product Information

Product Characteristics

- High Transparency
- Injection Molding
- Good Balance of Properties

Properties	Test Method	Unit	Typical Values
Physical Properties¹			
Melt Flow Rate (200°C @ 49N)	ISO 1133	g/10 min	8
Density (23°C)	ISO 1183	kg/m ³	1,020
Haze (2m mt)	ISO 14782	%	1.6
Mold Shrinkage (2m mt)	Internal Method	%	0.5
Mechanical Properties¹			
Tensile Strength at Yield	ISO 527-1,2	MPa	26
Tensile Strength at Break	ISO 527-1,2	MPa	19
Nominal Strain at Break	ISO 527-1,2	%	230
Flexural Modulus	ISO 178	MPa	1,530
Flexural Strength	ISO 178	MPa	31
Charpy Impact Strength (Notched)	ISO 179	KJ/m ²	3.5
Thermal Properties¹			
Vicat Softening Temperature 50N	ISO 306	°C	81
Deflection Temperature Under Load, 1.8 Mpa	ISO 75-1,2	°C	61

¹ Typical Properties; not to be construed as specifications. The data is intended as a general guideline only and does not necessarily represent the results that may be obtained otherwise.

Denka Clearen® is a registered trademark of Denki Kagaku Kogyo and is distributed by Calsak Corporation

Issued 9-1-13