# 

## Faraprene® TPE Resin - General Purpose

## 301-40A

### **Product Information**

#### **Product Characteristics**

• 39 Shore A

• General purpose injection molding grade elastomer

Properties	Test Method	Unit	<b>Typical Values</b>
Physical Properties <sup>1</sup>			
Melt Flow Rate			
230°C @ 5.0 kg load	ASTM D 1238	g/10min	9
Specific Gravity	ASTM D 792	-	1.16
Hardness, Shore A	ASTM D 2240	A-Scale	39
Mechanical Properties <sup>1</sup>			
Tensile Stress @ Break	ASTM D 412	psi	562
100% Modulus	ASTM D 412	psi	155
Elongation at Break	ASTM D 412	%	930
Tear Strength	ASTM D 624	psi	109

<sup>1</sup> Typical Properties; not to be construed as specifications. The data is intended as a general guideline only and does not necssarily

represent the results that may be obtained otherwise.

Faraprene® is a registered trademark of Oneil Color Corporation and is distributed by Calsak Corporation

Issued 9-1-13