

**Product Information****Product Characteristics**

- 50 Shore A
- General purpose injection molding grade elastomer

Properties	Test Method	Unit	Typical Values
<b>Physical Properties<sup>1</sup></b>			
Melt Flow Rate	230°C @ 2.16Kgf	ASTM D 1238	g/cm <sup>3</sup>
			5
Specific Gravity		ASTM D 792	-
			0.89
Hardness, Shore A		ASTM D 2240	A-Scale
			50
<b>Mechanical Properties<sup>1</sup></b>			
Tensile Stress @ Break		ASTM D 412	psi
			>800
100% Modulus		ASTM D 412	psi
			160
Elongation at Break		ASTM D 412	%
			>1000
Tear Strength		ASTM D 624	psi
			110

<sup>1</sup> Typical Properties; not to be construed as specifications. The data is intended as a general guideline only and does not necessarily represent the results that may be obtained otherwise.

Faraprene® is a registered trademark of Oneil Color Corporation and is distributed by Calsak Corporation

Issued 9-1-13