

### Product Information

#### Product Characteristics

- 14 Shore A
- FDA Compliant
- General purpose injection molding grade elastomer

Properties	Test Method	Unit	Typical Values	
<b>Physical Properties<sup>1</sup></b>				
Melt Flow Rate	230°C @ 5.0 kgf	ASTM D 1238	Dg/min	5
Specific Gravity		ASTM D 792	-	0.89
Hardness, Shore A		ASTM D 2240	A-Scale	14
<b>Mechanical Properties<sup>1</sup></b>				
Tensile Stress @ Break		ASTM D 412	psi	250
100% Modulus		ASTM D 412	psi	15
Elongation at Break		ASTM D 412	%	1,840

<sup>1</sup> Typical Properties; not to be construed as specifications. The data is intended as a general guideline only and does not necessarily represent the results that may be obtained otherwise.

Faraprene® is a registered trademark of Oneil Color Corporation and is distributed by Calsak Corporation

Issued 9-1-13