

Product Information

Product Characteristics

- Melt Processible Rubber
- 76 Shore A
- Blow Molding/Injection Molding/Extrusion/Vacuum Forming

Properties	Test Method	Unit	Typical Values
Physical Properties¹			
Specific Gravity	ASTM D 471	-	1.26
Durometer Hardness	ASTM D 2240	A-Scale	76
Mechanical Properties¹			
Tensile Stress	ASTM D 412	psi	769
Tensile Strength	ASTM D 412	psi	1440
Tensile Elongation	ASTM D 412	%	400
Tear Strength	ASTM D 624	lbf/in	190

¹ Typical Properties; not to be construed as specifications. The data is intended as a general guideline only and does not necessarily represent the results that may be obtained otherwise.

Alcryn® is a registered trademark of Advanced Polymer Alloys and is distributed by Calsak Corporation

Issued 9-1-13