

**Product Information****Product Characteristics**

- Melt Processible Rubber
- 79 Shore A
- Blow Molding/Injection Molding/Extrusion/Calendering

Properties	Test Method	Unit	Typical Values
<b>Physical Properties<sup>1</sup></b>			
Specific Gravity	ASTM D 792	-	1.17
Durometer Hardness	ASTM D 2240	A-Scale	79
<b>Mechanical Properties<sup>1</sup></b>			
Tensile Stress	ASTM D 412	psi	730
Tensile Strength	ASTM D 412	psi	2,000
Tensile Elongation	ASTM D 412	%	420
Tear Strength	ASTM D 624	lbf/in	250

<sup>1</sup> Typical Properties; not to be construed as specifications. The data is intended as a general guideline only and does not necessarily represent the results that may be obtained otherwise.

Alcryn® is a registered trademark of Advanced Polymer Alloys and is distributed by Calsak Corporation

Issued 9-1-13