

Duragrip® TPE Resin

# DGR 6030

## Product Information

### Product Characteristics

- Soft Touch TPE
- 33 Shore A
- Injection Molding & Extrusion

Properties	Test Method	Unit	Typical Values
<b>Physical Properties<sup>1</sup></b>			
Specific Gravity	ASTM D 792	-	0.99
Durometer Hardness	ASTM D 2240	A-Scale	33
<b>Mechanical Properties<sup>1</sup></b>			
Tensile Stress	ASTM D 412	psi	153
Tensile Strength	ASTM D 412	psi	635
Tensile Elongation	ASTM D 412	%	500
Tear Strength	ASTM D 624	lbf/in	81

<sup>1</sup> Typical Properties; not to be construed as specifications. The data is intended as a general guideline only and does not necessarily represent the results that may be obtained otherwise.

Duragrip® is a registered trademark of Advanced Polymer Alloys and is distributed by Calsak Corporation

Issued 9-1-13