

Duragrip® TPE Resin

DGR 6050

Product Information

Product Characteristics

- Soft Touch TPE
- 49 Shore A
- Injection Molding & Extrusion

Properties	Test Method	Unit	Typical Values
Physical Properties¹			
Specific Gravity	ASTM D 792	-	0.99
Durometer Hardness	ASTM D 2240	A-Scale	49
Mechanical Properties¹			
Tensile Stress	ASTM D 412	psi	298
Tensile Strength	ASTM D 412	psi	859
Tensile Elongation	ASTM D 412	%	450
Tear Strength	ASTM D 624	lbf/in	119

¹ Typical Properties; not to be construed as specifications. The data is intended as a general guideline only and does not necessarily represent the results that may be obtained otherwise.

Duragrip® is a registered trademark of Advanced Polymer Alloys and is distributed by Calsak Corporation

Issued 9-1-13