

Product Information

Product Characteristics

- High Impact
- Good Flow
- Injection Molding/Extrusion Grade

Properties	Test Method	Unit	Typical Values
Physical Properties¹			
Melt Flow Rate (230°C, 37.3N (3.8kgf))	ISO 1133	°C	4
Specific Gravity	ISO 1183	-	1.15
Mold Shrinkage	ISO 294-4	%	0.4-0.7
Rockwell Hardness M Scale	ISO 2039-2	-	50
Refractive Index	ISO 489	-	1.49
Light Transmission	ISO 13468-1	%	91
Haze	ISO 14782	%	1.1
Mechanical Properties¹			
Tensile Strength at Break	ISO 527-2	MPa	37
Tensile Strain at Break	ISO 527-2	%	74
Flexural Strength	ISO 178	MPa	61
Flexural Modulus	ISO 178	MPa	1,700
Charpy Impact Sgstrength	ISO 179-1	KJ/m ²	5.2
Thermal Properties¹			
Vicat Softening Temperature	ISO 306	°C	93
Deflection Temperature Under Load			
1.82MPa (annealed)	ISO 75-2	°C	85
Flammability	UL 94	-	HB

¹ Typical Properties; not to be construed as specifications. The data is intended as a general guideline only and does not necessarily represent the results that may be obtained otherwise.

Sumipex® is a registered trademark of Sumitomo Chemical and is distributed by Calsak Corporation