

SUMITOMO CHEMICAL CO LTD

TOKYO SUMITOMO TWIN BLDG, 27-1 SHINKAWA 2-CHOME, CHUO-KU, TOKYO 104-8260 JP

HT(h)

Polymethyl Methacrylate (PMMA), "SUMIPEX", furnished as pellets, powder, sheets

Color	Min Thk (mm)	Flame Class	HWI	HAI	RTI Elec	RTI Imp	RTI Str
ALL	1.5	HB	3	0	50	50	50
	3.0	HB	2	0	50	50	50

Comparative Tracking Index (CTI): -
 Dielectric Strength (kV/mm): -
 High-Voltage Arc Tracking Rate (HVTR): -
 Dimensional Stability (%): -
 Inclined Plane Tracking (IPT): -
 Volume Resistivity (10^x ohm-cm) : -
 High Volt, Low Current Arc Resis (D495): -

(h) - Two digits 00-99 incl. plus the letter X, Y or Z.

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 1985-07-24
 Last Revised: 2013-05-21

© 2013 UL LLC



IEC and ISO Test Methods

Test Name	Test Method	Units	Thickness Tested (mm)	Value
Flammability	IEC 60695-11-10	Class (color)	1.5	HB75 (ALL)
			3.0	HB40 (ALL)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	C	-	-
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	C	-	-
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-
IEC Ball Pressure	IEC 60695-10-2	C	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m ²	-	-
ISO Izod Impact	ISO 180	kJ/m ²	-	-
ISO Charpy Impact	ISO 179-2	kJ/m ²	-	-

© 2013 UL LLC