

TEIJIN POLYCARBONATE SINGAPORE PTE LTD

#01-01, 111 SAKRA AVE, SINGAPORE 627881 SG

L-1250U(#)(f1), L-1250V(#)(f1), L-1250Z(#)(f1)

Polycarbonate (PC), "Panlite", furnished as pellets, powder

Color	Min Thk (mm)	Flame Class	HWI	HAI	RTI		RTI Str
					Elec	Imp	
ALL	0.40	V-2	4	3	80	80	80
	0.84	V-2	4	3	80	80	80
	1.5	HB	4	0	125	115	125
	3.0	HB	1	0	125	115	125
	6.0	HB	1	0	125	115	125

Comparative Tracking Index (CTI): **2**

Inclined Plane Tracking (IPT): -

Dielectric Strength (kV/mm): **24**Volume Resistivity (10^x ohm-cm) : **16**High-Voltage Arc Tracking Rate
(HVTR): **4**High Volt, Low Current Arc Resis (D495): **5**

Dimensional Stability (%): 0

(#) - Suffix optional**(f1) - Suitable for outdoor use with respect to exposure to Ultraviolet Light, Water Exposure and Immersion in accordance with UL 746C.**

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 1999-07-29

Last Revised: 2013-04-02

© 2013 UL LLC

**IEC and ISO Test Methods**

Test Name	Test Method	Units	Thickness	
			Tested (mm)	Value
Flammability	IEC 60695-11-10	Class (color)	0.40	V-2 (ALL)
			0.84	V-2 (ALL)
			1.5	HB75 (ALL)
			3.0	HB40 (ALL)
			6.0	HB40 (ALL)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	C	-	-
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	C	-	-
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-
IEC Ball Pressure	IEC 60695-10-2	C	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m ²	-	-
ISO Izod Impact	ISO 180	kJ/m ²	-	-
ISO Charpy Impact	ISO 179-2	kJ/m ²	-	-

© 2013 UL LLC