



Quality Reinforced and Custom Colored Engineering Plastics
 1240 E. Glenwood Place ~ Santa Ana, CA 92707
 (714) 546-4667 ~ FAX (714) 546-0401

PROCESSING GUIDE

MATERIAL: MN66-FG20

PRE-PROCESS	DATA	UNITS
DRYING TEMPERATURE	175	F
DRYING TIME	2-4 ¹	hours
MAX MOISTURE IN PROCESS	0.20	%
DRYER DEWPOINT	0	F
SUGGESTED SHOT SIZE	50-80	%
THERMAL		
REAR TEMPERATURE	520-550	F
MIDDLE TEMPERATURE	520-560	F
FRONT TEMPERATURE	530-570	F
NOZZLE TEMPERATURE	540-560	F
PROCESSING (MELT) TEMPERATURE	530-570	F
MOLD TEMPERATURE	150-225	F
MECHANICAL		
INJECTION PRESSURE	10,000-18,000	psi
INJECTION RATE	MODERATE	
BACK PRESSURE	50-80	psi
SCREW SPEED	50-70	rpm
CLAMP TONNAGE		tons/square inch
SCREW L/D RATIO	--	
SCREW COMPRESSION RATIO	--	

¹ DESSICANT TYPE DRYER REQUIRED FOR THESE DRYING PARAMETERS. ALWAYS CHECK MOISTURE CONTENT BEFORE PROCESSING.