

Product Information**Product Characteristics**

- General Purpose
- Good Hardness
- Good Clarity

Properties	Test Method	Unit	Typical Values
Physical Properties¹			
Melt Flow Rate (200°C @ 49N)	ISO 1133	g/10 min	8
Density	ISO 1183	kg/m ³	1,020
Haze	ISO 14782	%	1.7
Mechanical Properties¹			
Tensile Strength at Yield	ISO 527-2	MPa	25
Tensile Strength at Break	ISO 527-2	MPa	18
Tensile Strain at Break	ISO 527-2	%	230
Flexural Modulus	ISO 178	MPa	1,590
Flexural Strength	ISO 178	MPa	31
Charpy Impact Strength	ISO 179	KJ/m ²	1.8
Thermal Properties¹			
Vicat Softening Temperature 10N	ISO 306	°C	80
Deflection Temperature Under Load, 1.8 Mpa	ISO 75-1,2	°C	60

¹ Typical Properties; not to be construed as specifications. The data is intended as a general guideline only and does not necessarily represent the results that may be obtained otherwise.

DenkaNSBC® is a registered trademark of Denki Kagaku Kogyo and is distributed by Calsak Corporation

Issued 9-1-13