

## El Pro® Polypropylene Resin

**P400S** 

## **Product Information**

## **Product Characteristics**

- Homopolymer
- Suitable for monofilament and flat yarn products
- FDA 21 CFR 177.1520

Properties	<b>Test Method</b>	Unit	<b>Typical Values</b>
Physical Properties <sup>1</sup>			
Melt Flow Rate (230°C @ 2.16 Kg)	ASTM D 1238	g/10 min	3.5
Density	ASTM D 1505	g/cm³	0.910
Rockwell Hardness	ASTM D 785	R-Scale	85
Gloss	ASTM D 2457	%	65
Mechanical Properties <sup>1</sup>			
Tensile Strength at Yield	ASTM D 638	kg/cm²	320
Tensile Strength at Break	ASTM D 638	kg/cm²	250
Elongation at Break	ASTM D 638	%	650
Flexural Modulus	ASTM D 790	kg/cm²	13,500
Notched Izod Impact	ASTM D 256	kg-cm/cm	4
Thermal Properties <sup>1</sup>			
Vicat Softening Point	ASTM D 1525	°C	155
Heat Distortion Temperature			
4.6 kg/cm	n <sup>2</sup> ASTM D 648	°C	110
18.5 kg/cm	n <sup>2</sup> ASTM D 648	°C	60
Flammability	UL 94	-	-

<sup>&</sup>lt;sup>1</sup> Typical Properties; not to be construed as specifications. The data is intended as a general guideline only and does not necssarily represent the results that may be obtained otherwise.

 ${\sf EI-Pro}^{\circledast} \ is \ a \ registered \ trademark \ of \ SCG \ Chemicals \ and \ is \ distributed \ by \ Calsak \ Corporation$