

## El Pro® Polypropylene Resin

## P700J

## **Product Information**

## **Product Characteristics**

- Homopolymer
- General Purpose Injection Molding
- FDA 21 CFR 177.1520

Properties		Test Method	Unit	<b>Typical Values</b>
Physical Properties <sup>1</sup>				
Melt Flow Rate (230°C @ 2.16 Kg)		ASTM D 1238	g/10 min	12
Density		ASTM D 1505	g/cm³	0.910
Rockwell Hardness		ASTM D 785	R-Scale	90
Gloss		ASTM D 2457	%	51
Mechanical Properties <sup>1</sup>				
Tensile Strength at Yield		ASTM D 638	kg/cm²	320
Tensile Strength at Break		ASTM D 638	kg/cm²	200
Elongation at Break		ASTM D 638	%	650
Flexural Modulus		ASTM D 790	kg/cm²	14,500
Notched Izod Impact		ASTM D 256	kg-cm/cm	3
Thermal Properties <sup>1</sup>				
Vicat Softening Point		ASTM D 1525	°C	155
Heat Distortion Temperature				
4.6 kg	/cm²	ASTM D 648	°C	110
18.5 kg	/cm²	ASTM D 648	°C	65
Flammability		UL 94	-	НВ

<sup>1</sup> Typical Properties; not to be construed as specifications. The data is intended as a general guideline only and does not necessarily

represent the results that may be obtained otherwise.

 $\mathsf{El}\operatorname{-\mathsf{Pro}}^{\circledast}$  is a registered trademark of SCG Chemicals and is distributed by Calsak Corporation

Issued 9-1-13