

## El Pro® Polypropylene Resin

## P840J

## **Product Information**

## **Product Characteristics**

- Impact Copolymer for Injection Molding
- High Stiffness
- FDA 21 CFR 177.1520

Properties	<b>Test Method</b>	Unit	<b>Typical Values</b>
Physical Properties <sup>1</sup>			
Melt Flow Rate (230°C @ 2.16 Kg)	ASTM D 1238	g/10 min	43
Density	ASTM D 1505	g/cm³	0.910
Rockwell Hardness	ASTM D 785	R-Scale	75
Gloss	ASTM D 2457	%	30
Mechanical Properties <sup>1</sup>			
Tensile Strength at Yield	ASTM D 638	kg/cm²	290
Tensile Strength at Break	ASTM D 638	kg/cm²	180
Elongation at Break	ASTM D 638	%	50
Flexural Modulus	ASTM D 790	kg/cm²	12,500
Notched Izod Impact	ASTM D 256	kg-cm/cm	6.5
Thermal Properties <sup>1</sup>			
Vicat Softening Point	ASTM D 1525	°C	150
Heat Distortion Temperature			
4.6 kg/cr	n² ASTM D 648	°C	110
18.5 kg/cr	n² ASTM D 648	°C	55
Flammability	UL 94	-	HB

<sup>1</sup> Typical Properties; not to be construed as specifications. The data is intended as a general guideline only and does not necssarily

represent the results that may be obtained otherwise.

 $\mathsf{El}\operatorname{-\mathsf{Pro}}^{\circledast}$  is a registered trademark of SCG Chemicals and is distributed by Calsak Corporation

Issued 9-1-13