

## Polylac® ABS Resin - General Purpose

**PA-707** 

## **Product Information**

## **Product Characteristics**

- High Gloss
- High Rigidity
- Medium Flow

Properties	Test Method	Unit	Typical Values
Physical Properties <sup>1</sup>			
Melt Flow Rate (200°C @ 5.0 Kg)	ASTM D 1238	g/10 min	1.7
(220°C @ 10.0 Kg)	ISO 1133	g/10 min	23
Vicat Softening Point	ASTM D 1525	°F	221
Specific Gravity	ASTM D 792	-	1.06
Mold Shrinkage	ASTM D 955	in/in	.005008
Rockwell Hardness	ASTM D 785	R-Scale	R-116
Mechanical Properties <sup>1</sup>			
Tensile Strength at Yield, Type I, 1/8"	ASTM D 638	psi	6,950
Tensile Elongation At Break	ASTM D 638	%	20
Flexural Modulus, Type I, 1/8"	ASTM D 790	psi	410,000
Flexural Strength, Type I, 1/8"	ASTM D 790	psi	12,200
Notched Izod 1/8" @ 73°F	ASTM D 256	ft-lbs/in	2.9
1/4" @ 73°F	ASTM D 256	ft-lbs/in	2.7
Thermal Properties <sup>1</sup>			
Heat Distortion Temperature @ 264 psi 1/8"			
Annealed	ASTM D 648	°F	203
Unannealed	ASTM D 648	°F	186
Flammability	UL 94	-	НВ

<sup>&</sup>lt;sup>1</sup> Typical Properties; not to be construed as specifications. The data is intended as a general guideline only and does not necssarily represent the results that may be obtained otherwise.