

## Polylac® ABS Resin - High Flow

**PA-716** 

## **Product Information**

## **Product Characteristics**

- High Flow
- Medium Impact
- Injection Grade

| Properties                                 | <b>Test Method</b> | Unit      | <b>Typical Values</b> |
|--|--------------------|-----------|-----------------------|
| Physical Properties <sup>1</sup>           |                    |           |                       |
|  |                    |           |                       |
| Melt Flow Rate (200°C @ 5.0 Kg)            | ASTM D 1238        | g/10 min  | 3.5                   |
| (220°C @ 10.0 Kg)                          | ISO 1133           | g/10 min  | 38                    |
| Vicat Softening Point                      | ASTM D 1525        | °F        | 221                   |
| Specific Gravity                           | ASTM D 792         | -         | 1.04                  |
| Mold Shrinkage                             | ASTM D 955         | in/in     | .005008               |
| Rockwell Hardness                          | ASTM D 785         | R-Scale   | R-112                 |
| Mechanical Properties <sup>1</sup>         |                    |           |                       |
| Tensile Strength at Yield, Type I, 1/8"    | ASTM D 638         | psi       | 6,320                 |
| Tensile Elongation At Break                | ASTM D 638         | %         | 25                    |
| Flexural Modulus, Type I, 1/8"             | ASTM D 790         | psi       | 340,000               |
| Flexural Strength, Type I, 1/8"            | ASTM D 790         | psi       | 9,920                 |
| Notched Izod 1/8" @ 73°F                   | ASTM D 256         | ft-lbs/in | 4.5                   |
| 1/4" @ 73°F                                | ASTM D 256         | ft-lbs/in | 4                     |
| Thermal Properties <sup>1</sup>            |                    |           |                       |
|  |                    |           |                       |
| Heat Distortion Temperature @ 264 psi 1/8" |                    |           |                       |
| Annealed                                   | ASTM D 648         | °F        | 203                   |
| Unannealed                                 | ASTM D 648         | °F        | 186                   |
| Flammability                               | UL 94              | -         | НВ                    |

<sup>&</sup>lt;sup>1</sup> Typical Properties; not to be construed as specifications. The data is intended as a general guideline only and does not necssarily represent the results that may be obtained otherwise.