

## Polylac® ABS Resin - General Purpose

## PA-747

## **Product Information**

## **Product Characteristics**

- Ultra High Impact
- Injection Grade
- NSF 14

Properties	Test Method	Unit	<b>Typical Values</b>
Physical Properties <sup>1</sup>			
Melt Flow Rate (200°C @ 5.0 Kg)	ASTM D 1238	g/10 min	1.1
(220°C @ 10.0 Kg)	ISO 1133	g/10 min	13
Vicat Softening Point	ASTM D 1525	۴F	217
Specific Gravity	ASTM D 792	-	1.03
Mold Shrinkage	ASTM D 955	in/in	.005008
Rockwell Hardness	ASTM D 785	R-Scale	R-108
Mechanical Properties <sup>1</sup>			
Tensile Strength at Yield, Type I, 1/8"	ASTM D 638	psi	5,470
Tensile Elongation At Break	ASTM D 638	%	30
Flexural Modulus, Type I, 1/8"	ASTM D 790	psi	310,000
Flexural Strength, Type I, 1/8"	ASTM D 790	psi	8,800
Notched Izod 1/8" @ 73°F	ASTM D 256	ft-lbs/in	7.5
1/4" @ 73°F	ASTM D 256	ft-lbs/in	5.9
Thermal Properties <sup>1</sup>			
Heat Distortion Temperature @ 264 psi 1/8"			
Annealed	ASTM D 648	°F	203
Unannealed	ASTM D 648	°F	186
Flammability	UL 94	-	HB

<sup>1</sup> Typical Properties; not to be construed as specifications. The data is intended as a general guideline only and does not necssarily

represent the results that may be obtained otherwise.

Polylac® is a registered trademark of Chi Mei Corporation and is distributed by Calsak Corporation