

## Product Information

### Product Characteristics

- Medium Impact
- High Flow
- TBBA Based

| Properties                                 | Test Method | Unit      | Typical Values |
|--|-------------|-----------|----------------|
| <b>Physical Properties<sup>1</sup></b>     |             |           |                |
| Melt Flow Rate (200°C @ 5.0 Kg)            | ASTM D 1238 | g/10 min  | 4.6            |
| (220°C @ 10.0 Kg)                          | ISO 1133    | g/10 min  | 46             |
| Vicat Softening Point                      | ASTM D 1525 | °F        | 198            |
| Specific Gravity                           | ASTM D 792  | -         | 1.17           |
| Mold Shrinkage                             | ASTM D 955  | in/in     | .005-.008      |
| Rockwell Hardness                          | ASTM D 785  | R-Scale   | R-101          |
| <b>Mechanical Properties<sup>1</sup></b>   |             |           |                |
| Tensile Strength at Yield, Type I, 1/8"    | ASTM D 638  | psi       | 5,670          |
| Tensile Elongation At Break                | ASTM D 638  | %         | 20             |
| Flexural Modulus, Type I, 1/8"             | ASTM D 790  | psi       | 320,000        |
| Flexural Strength, Type I, 1/8"            | ASTM D 790  | psi       | 9,070          |
| Notched Izod 1/8" @ 73°F                   | ASTM D 256  | ft-lbs/in | 4.4            |
| 1/4" @ 73°F                                | ASTM D 256  | ft-lbs/in | 3.7            |
| <b>Thermal Properties<sup>1</sup></b>      |             |           |                |
| Heat Distortion Temperature @ 264 psi 1/8" |             |           |                |
| Annealed                                   | ASTM D 648  | °F        | 185            |
| Unannealed                                 | ASTM D 648  | °F        | 169            |
| Flammability                               | UL 94       | 1.5mm     | V-1            |
|  | UL 94       | 2.5mm     | V0             |
|  | UL 94       | 2.5mm     | 5VA            |

<sup>1</sup> Typical Properties; not to be construed as specifications. The data is intended as a general guideline only and does not necessarily represent the results that may be obtained otherwise.

Polylac® is a registered trademark of Chi Mei Corporation and is distributed by Calsak Corporation

Issued 9-1-13