

Polyrex® Polystyrene Resin - General Purpose

**PG-383** 

## **Product Information**

## **Product Characteristics**

- General Purpose
- Extrusion
- High Strength

Properties	<b>Test Method</b>	Unit	<b>Typical Values</b>
Physical Properties <sup>1</sup>			
Melt Flow Rate (200°C @ 5.0 Kg)	ASTM D 1238	g/10 min	2.2
(230°C @ 3.8 Kg)	ASTM D 1238	g/10 min	8.5
Specific Gravity	ASTM D 792	-	1.05
Rockwell Hardness	ASTM D 785	M-Scale	M-82
Mechanical Properties <sup>1</sup>			
Tensile Strength at Yield, Type I, 1/8"	ASTM D 638	psi	7,810
Tensile Elongation At Break	ASTM D 638	%	2
Flexural Modulus, Type I, 1/8"	ASTM D 790	psi	470,000
Flexural Strength, Type I, 1/8"	ASTM D 790	psi	11,650
Notched Izod 1/8" @ 73°F	ASTM D 256	ft-lbs/in	0.33
1/4" @ 73°F	ASTM D 256	ft-lbs/in	0.31
Thermal Properties <sup>1</sup>			
Vicat Softening Point	ASTM D 1525	°F	221
Heat Distortion Temperature @ 264 psi 1/8"			
Annealed	ASTM D 648	°F	210
Unannealed	ASTM D 648	°F	192
Flammability	UL 94	-	НВ

<sup>&</sup>lt;sup>1</sup> Typical Properties; not to be construed as specifications. The data is intended as a general guideline only and does not necssarily represent the results that may be obtained otherwise.