

Product Information

Product Characteristics

- Super High Heat
- Extrusion Grade
- Good Overall Strength

Properties	Test Method	Unit	Typical Values
Physical Properties¹			
Melt Flow Rate (200°C @ 5.0 Kg)	ASTM D 1238	g/10 min	2.6
(230°C @ 3.8 Kg)	ASTM D 1238	g/10 min	8.5
Specific Gravity	ASTM D 792	-	1.05
Rockwell Hardness	ASTM D 785	M-Scale	M-50
Mechanical Properties¹			
Tensile Strength at Yield, Type I, 1/8"	ASTM D 638	psi	3,700
Tensile Elongation At Break	ASTM D 638	%	55
Flexural Modulus, Type I, 1/8"	ASTM D 790	psi	270,000
Flexural Strength, Type I, 1/8"	ASTM D 790	psi	5,110
Notched Izod 1/8" @ 73°F	ASTM D 256	ft-lbs/in	2.75
1/4" @ 73°F	ASTM D 256	ft-lbs/in	2
Thermal Properties¹			
Vicat Softening Point	ASTM D 1525	°F	212
Heat Distortion Temperature @ 264 psi 1/8"			
Annealed	ASTM D 648	°F	201
Unannealed	ASTM D 648	°F	176
Flammability	UL 94	-	HB

¹ Typical Properties; not to be construed as specifications. The data is intended as a general guideline only and does not necessarily represent the results that may be obtained otherwise.

Polyrex® is a registered trademark of Chi Mei Corporation and is distributed by Calsak Corporation

Issued 9-1-13