

### Product Information

#### Product Characteristics

- General Purpose Injection Molding Grade
- High Rigidity
- Medium Flow

Properties	Test Method	Unit	Typical Values
<b>Physical Properties<sup>1</sup></b>			
Melt Flow Rate (200°C @ 5.0 Kg)	ASTM D 1238	g/10 min	2.8
(230°C @ 3.8 Kg)	ASTM D 1238	g/10 min	14
Vicat Softening Point	ASTM D 1525	°F	219
Specific Gravity	ASTM D 792	-	1.06
Mold Shrinkage	ASTM D 955	in/in	.002-.004
Rockwell Hardness	ASTM D 785	M-Scale	M-83
<b>Mechanical Properties<sup>1</sup></b>			
Tensile Strength at Yield, Type I, 1/8"	ASTM D 638	psi	9,920
Tensile Elongation At Break	ASTM D 638	%	5
Flexural Modulus, Type I, 1/8"	ASTM D 790	psi	500,000
Flexural Strength, Type I, 1/8"	ASTM D 790	psi	14,200
Notched Izod 1/8" @ 73°F	ASTM D 256	ft-lbs/in	0.33
1/4" @ 73°F	ASTM D 256	ft-lbs/in	0.31
<b>Thermal Properties<sup>1</sup></b>			
Heat Distortion Temperature @ 264 psi 1/4"			
Annealed	ASTM D 648	°F	212
Unannealed	ASTM D 648	°F	194
Flammability	UL 94	-	HB

<sup>1</sup> Typical Properties; not to be construed as specifications. The data is intended as a general guideline only and does not necessarily represent the results that may be obtained otherwise.