

Product Information

Product Characteristics

- High Heat
- Chemical Resistant
- Great Overall Strength

Properties	Test Method	Unit	Typical Values
Physical Properties¹			
Melt Flow Rate (200°C @ 5.0 Kg)	ASTM D 1238	g/10 min	0.9
(230°C @ 3.8 Kg)	ASTM D 1238	g/10 min	4.5
Vicat Softening Point	ASTM D 1525	°F	226
Specific Gravity	ASTM D 792	-	1.06
Mold Shrinkage	ASTM D 955	in/in	.002-.004
Rockwell Hardness	ASTM D 785	M-Scale	M-85
Mechanical Properties¹			
Tensile Strength at Yield, Type I, 1/8"	ASTM D 638	psi	11,350
Tensile Elongation At Break	ASTM D 638	%	7
Flexural Modulus, Type I, 1/8"	ASTM D 790	psi	540,000
Flexural Strength, Type I, 1/8"	ASTM D 790	psi	17,000
Notched Izod 1/8" @ 73°F	ASTM D 256	ft-lbs/in	0.44
1/4" @ 73°F	ASTM D 256	ft-lbs/in	0.37
Thermal Properties¹			
Heat Distortion Temperature @ 264 psi 1/4"			
Annealed	ASTM D 648	°F	217
Unannealed	ASTM D 648	°F	201
Flammability	UL 94	-	HB

¹ Typical Properties; not to be construed as specifications. The data is intended as a general guideline only and does not necessarily represent the results that may be obtained otherwise.