

**CHI MEI CORPORATION**

59-1 SAN CHIA, JEN TE, TAINAN 717 TW

**PW-997S(+)**

Acrylate Styrene Acrylonitrile (ASA), "KIBILAC", furnished as pellets

Color	Min Thk (mm)	Flame Class	HWI	HAI	RTI Elec	RTI Imp	RTI Str
ALL	1.5	HB	4	0	50	50	50
	3.0	HB	3	0	50	50	50

Comparative Tracking Index (CTI): 0

Inclined Plane Tracking (IPT): -

Dielectric Strength (kV/mm): -

Volume Resistivity (10<sup>x</sup> ohm-cm): -High-Voltage Arc Tracking Rate  
(HVTR): 3

High Volt, Low Current Arc Resis (D495): 6

Dimensional Stability (%): -

(+) - Optional prefix or suffix; may be used to denote usage of 0-0.5 percent acid scavengers. For PC-110(+), Optional the suffix except L, N, U, V, T, and F. For Grades PC-6015(+), PB-1202(+), Maybe none or replace by one alphabet to indicate the color.

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 2006-08-31

Last Revised: 2007-11-27

© 2013 UL LLC

**IEC and ISO Test Methods**

Test Name	Test Method	Units	Thickness	
			Tested (mm)	Value
Flammability	IEC 60695-11-10	Class (color)	1.5	HB75 (ALL)
			3.0	HB40 (ALL)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	C	-	-
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	C	-	-
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-
IEC Ball Pressure	IEC 60695-10-2	C	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m <sup>2</sup>	-	-
ISO Izod Impact	ISO 180	kJ/m <sup>2</sup>	-	-
ISO Charpy Impact	ISO 179-2	kJ/m <sup>2</sup>	-	-

© 2013 UL LLC