

AR film (Conductive Grade)

Film Cross Sectional Structure

1 st layer	Top Coating (0.01um)
2 nd layer	AR Sputter layer(0.01um)
3 rd layer	Hardcoat Base (5-6um)
4 th layer	PET base film (188um)
5 th layer	Adhesive layer(25um)
6 th layer	Release Liner(75um)

Reflectance: 5% Max
 Transmittance: 50% - 80%
 Surface resistivity: 1000 ohms/square Max
 Pensile test: 3H

