

Product Information

Product Characteristics

- Injection Molding Grade
- Automotive
- Easy Processibility

Properties	Test Method	Unit	Typical Values
Physical Properties¹			
Density	ISO 1183	kg/m ³	1,140
Mold Shrinkage	In House Method	% Parallel	0.5-0.7
		% Across	0.5-0.7
Mechanical Properties¹			
Tensile Modulus 1mm/min	ISO 527	MPa	2,250
Tensile Yield Stress 50mm/min	ISO 527	MPa	56
Flexural Modulus 2mm/min	ISO 178	MPa	2,300
Flexural Strength 2mm/min	ISO 178	MPa	85
Charpy Impact Strength		Unnotched	NB
		Notched	80
Thermal Properties¹			
Heat Deflection Temperature	ISO 75-1,2		
		1.80MPa	°C
		0.45MPa	°C
Vicat Softening Temperature	ISO 306	50°C/h 50N	122
Flammability	UL 94	-	
	UL 94	-	

¹ Typical Properties; not to be construed as specifications. The data is intended as a general guideline only and does not necessarily represent the results that may be obtained otherwise.

Multilon® is a registered trademark of Teijin Chemicals and is distributed by Calsak Corporation

Issued 9-1-13